


Goodspeed INDOOR retopping (Formerly known as PORPLASTIC INDOOR retopping)



Performance check







Goodspeed

Layer	Consumption	Thickness	Application
LINE PAINT Goodspeed X8005	10 – 15 g/lfm	ca. 0.10 - 0.20mm	Roller or brush
FLEXIBLE TOP FINISH Goodspeed \$6000P	0.10 – 0.13 kg/m²	ca. 0.05 – 0.10 mm	roller
SELF LEVELING LAYER Goodspeed C524	ca. 2.8 kg/m²	ca. 2 mm	Notched trowel

Preparation

- Clean old surface thoroughly Any damages (splits etc.) must be repaired
- Abrade surface with abrasive paper (24 or 36)
- Remove dust with industrial vacuum cleaner
- Remove last traces of dust by wiping with damp cloth, if necessary
- Surface must be absolutely dry, clean and free from dust or any substance that could inhibit adhesion
- Retopping in the same system build-up as the existing coating

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all Goodspeed data sheets are updated on a regular basis it is the users' responsibility to obtain the most recent issue (see www.porplastic.com or contact us directly). Date of issue: June 2025 – all technical information is subject to change without prior notice.



