

Goodspeed Molympic gold (Formerly known as PORPLASTIC Molympic gold)

Massive, one or multilayer full PU-bound system. All layers with coloured and virgin EPDM granules, water-impermeable

WORLD-CLASS SPORTS SURFACE











Application Fields

Running tracks

Run up tracks


Athletic sport areas type A,B,C

Short distance tracks


High-performance sport

International competitions

Olympia, world championships









Environmentally Friendly



Very Durable

Performance check



WA certified 14.5 mm



Tensile strength of 0.56 N/mm²



Vertical deformation of 2.00 mm



Shock absorption



Friction of 74



Resistance to wear of 1.62g



Elongation at break



Spike resistance



Available in many colours









Goodspeed

Layer	Consumption	Thickness	Application
LINE PAINT Goodspeed X8090	20 −30 g/lfm	ca. 0.10 – 0.20 mm	Spray
UV-SEALER (optional) Goodspeed S6020	0.17 –0.20 per layer	ca. 0.10 mm	Spray, In 2 layers
WEARING LAYER Goodspeed C570 Goodspeed EPDM (1 – 4mm)	ca. 2.80 kg/m² 2.80 net 4.00 total	ca. 3 –5 mm	Notched squeegee, broadcast, remove excess
2. CAST COATING Goodspeed C570 Goodspeed EPDM (1 - 4mm)	ca. 3 kg/m² 3.00 net 3.50 total	ca. 5 mm	Notched squeegee, broadcast, remove excess
1. CAST COATING Goodspeed C570 Goodspeed EPDM (1 - 4mm)	3 – 3.50 kg/m² 3.00net 3.50 total	ca. 5 mm	Notched squeegee, broadcast, remove excess
PRIMER Goodspeed P270 (for asphalt)	0.15 – 0.20 kg/m²	ca. 0.10 mm	Roll or spray

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all Goodspeed data sheets are updated on a regular basis it is the users' responsibility to obtain the most recent issue (see www.porplastic.com or contact us directly). Date of issue: June 2025 – all technical information is subject to change without prior notice.











