

Goodspeed *M olympic ultra*

(Formerly known as PORPLASTIC M olympic ultra)

Only two-layer full PU-bond system with coloured EPDM granules, water-impermeable

ULTIMATE SPORT SURFACE

Application Fields

Running tracks

Run up tracks

Athletic sport areas type A,B,C

Short distance tracks

High-performance sport

International competitions

Olympia, world championships



WA Certified



Only 2 Layers



Ultra Robust

Performance check



WA certified
14.1 mm



Shock absorption
42%



Ultra elongation at
break of 106%



Ultra robust
tensile strength
0.64 N/mm²



Friction of 0.67



Spike resistance



Vertical deformation
of 2.20 mm









Environmentally
friendly



Available in many
colours



Layer		Consumption	Thickness	Application
LINE PAINT Goodspeed X8090		20 –30 g/lfm	ca. 0.10 – 0.20 mm	Spray
UV-SEALER (optional) Goodspeed S6020		0.17 –0.20 per layer	ca. 0.10 mm	Spray, In 2 layers
WEARING LAYER Goodspeed C555 Goodspeed EPDM (1 – 4mm)		ca. 3kg/m ² 3.00 net 4.00 total	ca. 3 –5 mm	Notched squeegee, broadcast, remove excess
ELASTIC LAYER Goodspeed C550 Goodspeed SBR (1 – 4mm)		ca. 2.50 – 3 kg/m ² 3.50net 4.50 total	ca. 10 mm	Notched squeegee, broadcast, remove excess
PORE SEALER Goodspeed L370		1.10 – 1.80 kg/m ² 3.00net 3.50 total	ca. 0.10 – 0.20 mm	Squeegee, or paving machine with trowel bar
PRIMER (optional) Goodspeed P270 (for asphalt)		0.15 – 0.20 kg/m ²	ca. 0.10 mm	Roll or spray

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all Goodspeed data sheets are updated on a regular basis it is the users' responsibility to obtain the most recent issue (see www.porplastic.com or contact us directly). Date of issue: June 2025 – all technical information is subject to change without prior notice.

