

## Goodspeed TENNIS comfort pro

(Formerly known as PORPLASTIC TENNIS comfort pro)

Tennis court flooring system for indoor and outdoor pointelastic according to EN 14904, ITF classified





## Performance check









## Goodspeed

Layer	Consumption	Thickness	Application
LINE PAINT Goodspeed X8085 SR	20 – 30 g/lfm	ca. 0.10 - 0.20 mm	Roller or brush
STRUCTURED TOP FINISH Goodspeed \$6095 \$R	150 – 200g per layer (in 2 layers)	ca. 0.30 mm	Rubber squeegee
SELF LEVELING LAYER Goodspeed C524	ca. 2.00 kg/m²	ca. 1.50 mm	Notched squeegee
ELASTIC MAT Goodspeed basic L390 M	4.50 – 7.50 kg/m²	ca. 6 – 10 mm	Notched squeegee
PRIMER FLOORFINDER EP-P210	ca. 0.40 kg/m²	ca. 0.20 mm	Roller or rubber squeegee

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all Goodspeed data sheets are updated on a regular basis it is the users' responsibility to obtain the most recent issue (see www.porplastic.com or contact us directly). Date of issue: June 2025 – all technical information is subject to change without prior notice.











